PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 :		(11) International Publication Number: WO 92/18542
C08B 31/18, C07H 7/033 C11D 3/22, D21H 17/28	A1	(43) International Publication Date: 29 October 1992 (29.10.92)

(21) International Application Number: PCT/EP92/00827

(22) International Filing Date: 13 April 1992 (13.04.92)

(30) Priority data:
T091A000281 12 April 1991 (12.04.91) IT

(71) Applicant *(for all designated States except US)*: NOVAMONT S.P.A. [IT/IT]; Foro Buonaparte, 31, I-20121 Milano (IT).

(72) Inventors; and
(75) Inventors/Applicants *(for US only)* : CONCA, Esterino [IT/IT]; Via Montegrappa, 8, I-28100 Novara (IT). BRUSSANI, Gianfranco [IT/IT]; Via Don Cabrio, 31, I-13051 Biella (IT).

(74) Agents: RAMBELLI, Paolo et al.; Jacobacci-Casetta & Perani S.p.A., Via Alfieri, 17, I-10121 Torino (IT).

(81) Designated States: AT (European patent), AU, BE (European patent), BG, BR, CA, CH (European patent), CS, DE (European patent), DK (European patent), ES (European patent), FI, FR (European patent), GB (European patent), GR (European patent), HU, IT (European patent), JP, KR, LU (European patent), MC (European patent), NL (European patent), NO, PL, RO, RU, SE (European patent), US.

Published
With international search report.

(54) Title: A METHOD OF OXIDISING CARBOHYDRATES

(57) Abstract

In a method of oxidising carbohydrates, particularly starch and dextrin, the oxidation is effected by molecular oxygen in an alkaline aqueous medium in the presence of a catalytic quantity of a metal ion selected from the metals of group VIII of the periodic table, copper or silver and a substance which acts as a ligand for the metal ion and is preferably constituted by a polydentate amine ligand.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria
AU	Australia
BB	Barbados
BE	Belgium
BF	Burkina Faso
BG	Bulgaria
BJ	Benin
BR	Brazil
CA	Canada
CF	Central African Republic
CG	Congo
CH	Switzerland
CI	Côte d'Ivoire
CM	Cameroon
CS	Czechoslovakia
DE	Germany
DK	Denmark
ES	Spain
FI	Finland
FR	France
GA	Gabon
GB	United Kingdom
GN	Guinea
GR	Greece
HU	Hungary
IE	Ireland
IT	Italy
JP	Japan
KP	Democratic People's Republic of Korea
KR	Republic of Korea
LI	Liechtenstein
LK	Sri Lanka
LU	Luxembourg
MC	Monaco
MG	Madagascar
ML	Mali
MN	Mongolia
MR	Mauritania
MW	Malawi
NL	Netherlands
NO	Norway
PL	Poland
RO	Romania
RU	Russian Federation
SD	Sudan
SE	Sweden
SN	Senegal
SU	Soviet Union
TD	Chad
TG	Togo
US	United States of America

A method of oxidising carbohydrates

The present invention relates to a method of oxidising carbohydrates, particularly starches, dextrin and hydrolysis products thereof.

Oxidised starches are used widely in the paper and textile industries. The product is generally produced by treating starch with hypochlorite in an alkaline aqueous medium. Alternatively, oxidised starches are produced by oxidation with periodate which can cleave the glucoside unit of starch between the C-2 and C-3 atoms which are converted into aldehyde groups. The starch thus produced is used mainly in the production of paper which retains good mechanical strength when wet.

A further potential application of oxidised starch or cellulose, described in German patent application DE-A-24 36 843 is its use as a builder for detergents. The products produced by oxidation with hypochlorite or periodate and subsequently with chlorite contain many carboxylic groups in a chain and thus have good sequestering powers. Their use is limited, however, by the fact that these substances are less biodegradable the higher their degree of oxidation.

The main object of the present invention is to provide an oxidation method which is particularly cheap and advantageous as regards the reagents used in the method. A further object is to provide a method which, with particular reference to the oxidation of starches, gives rise to an oxidation product with improved biodegradability characteristics.

This object is achieved by a method of oxidising carbohydrates, characterised in that the oxidation is effected by means of an oxygen containing gas in an alkaline aqueous medium in the presence of a catalytic quantity of a metal ion selected from the metals of group VIII of the periodic table, copper and silver and a substance which acts as a ligand for the metal ion.

Carbohydrates, which constitute the substrate to which the oxidation method of the invention is applied, include starch, hydrolysis products thereof with up to 1 glucoside unit, and simple carbohydrates such as sorbitol.

The term starch essentially means starch which has not been modified chemically and thus includes carbohydrates of natural and vegetable origin in general which are composed essentially of amylose and/or amylopectin. Native starches extracted from various plants such as potatoes, rice, tapioca, maize and cereals may be used. Of these, maize starch is preferred. Hydrolysis products of starch are constituted by mixtures of oligomers with various numbers of glucoside units, including glucose monomer. These hydrolysis products are easily obtainable, for example, by enzymatic hydrolysis, preferably with the use of endoenzymes. Substrates usable for the invention also include polyols with carbohydrate structure, such as sorbitol.

The metal ion used is preferably iron, copper, silver, cobalt or nickel and is introduced into the alkaline aqueous medium by means of a soluble salt, preferably constituted by a chloride or a sulphate.

Typically, the metal ion is used in a molar ratio of between 1 and 0.25% with reference to the number of moles of glucoside units in the substrate.

The ligand for the metal ion is preferably a polydentate amine ligand. Of these the following are contemplated:

- monoamines of the general formula:



in which one of the radicals R_1, R_2 and R_3 is selected from the group consisting of hydrogen, C_1-C_4 alkyl groups and carboxyalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms, and the rest of the R_1, R_2 or R_3 radicals are the same or different carboxyalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms, and

- polyamines of the general formula:



in which R is an alkylene group with from 1 to 4 carbon atoms, preferably ethylene, and

R_1, R_2, R_3, and R_4 are the same or different and are radicals selected independently of each other from the

group consisting of hydrogen, C_1-C_4 alkyl groups, aminoalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms and carboxyalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms,

or alternatively, R_1 and R_2 and/or R_3 and R_4 form a heterocyclic ring with the respective nitrogen atom,

or alternatively, R_1, R_2, R_3 and R_4 form heterocyclic groups with the respective nitrogen atoms. Of the preferred amine and polyamine ligands, nitrilotriacetic acid, iminodiacetic acid, ethylenediamine, diethylenetriamine, triethylenetetramine, ethylenediaminetetra-acetic acid (EDTA), ethylenediaminetriacetic acid, phenanthroline and 2,2'-dipyridyl are contemplated in particular.

A combination of EDTA with ferrous sulphate or ferrous chloride is particularly advantageous for the oxidation of starch and hydrolysis products thereof, including glucose.

The oxidation reaction is carried out by bubbling molecular oxygen or air through the alkaline aqueous medium which generally has a pH of from 8 to 14 and typically between 8 and 10 at a temperature of from 25 to 90°C and at atmospheric pressure with vigorous stirring.

Example 1.

40 g of dextrin was dissolved in 500 ml of deionised water. 0.63 g of $FeCl_2$ and 0.5 g of o-phenanthroline were added. The reaction was carried out at 60°C and at a pH of 9 in an atmosphere of oxygen and good stirring was maintained. A total of 15 ml of 3.4M

NaOH was introduced during a reaction period of 8 hours. Upon completion of the reaction the water was evaporated and the product recovered.

Example 2.

40 g of dextrin was dissolved in 500 ml of deionised water. 0.68 g of $FeSO_4.7H_2O$ and 0.5 g of o-phenanthroline were added. The reaction was carried out at 70°C and at a pH of 9 in an atmosphere of oxygen and good stirring was maintained.

A total of 35 ml of 3.4M NaOH was introduced during a reaction period of 12 hours. Upon completion of the reaction, the water was evaporated and the product recovered.

Example 3.

40 g of dextrin was dissolved in 500 ml of deionised water. 0.34 g of $FeSO_4.7H_2O$ and 25 g of o-phenanthroline were added. The reaction was carried out at 70°C and at a pH of 9 in an atmosphere of oxygen and good stirring was maintained.

A total of 60 ml of 3.4M NaOH was introduced during a reaction period of 32 hours. Upon completion of the reaction the water was evaporated and the product recovered.

Example 4.

40 g of dextrin was dissolved in 500 ml of deionised water. 0.34 g of $FeSO_4.7H_2O$ and 0.43 g of the dihydrated disodium salt of EDTA were added. The

reaction was carried out at 70°C and at a pH of 9 in an atmosphere of oxygen and good stirring was maintained.

A total of 60 ml of 3.4M NaOH was introduced during a reaction period of 16 hours. Upon completion of the reaction the water was evaporated and the product recovered.

Example 5.

20 g of soluble starch was dissolved in 500 ml of deionised water. 0.34 g of $FeSO_4.7H_2O$ and 0.25 g of o-phenanthroline were added. The reaction was carried out at 70°C and at a pH of 9 in an atmosphere of oxygen and good stirring was maintained.

A total of 17 ml of 3.4M NaOH was introduced during a reaction period of 12 hours. Upon completion of the reaction the water was evaporated and the product recovered.

Example 6.

20 g of maize starch was gelled in 500 ml of deionised water. 0.34 g of $FeSO_4.7H_2O$ and 0.46 g of EDTA were added in an atmosphere of oxygen and good stirring was maintained.

A total of 17 ml of 3.4M NaOH was introduced during a reaction period of 17 hours. Upon completion of the reaction the water was evaporated and the product recovered.

The recovered product was subjected to Ft-IR spectroscopy with Perkin Elmer 1760 equipment. The

graph below shows the spectra of the oxidation product (2) and of untreated starch (1) in Nujol.

The spectrum (2) has a band at a wavelength of 1597 cm^{-1} which is characteristic of the salified carboxyl group and is absent from the spectrum (1). The two spectra have substantially corresponding shapes in the region between 1000 and 1100 cm^{-1} in which there are strong bands characteristic of the structure of starch.

The oxidation product of a starch or a dextrin obtainable by the method which is described above and is the subject of the following claims falls within the scope of the present invention.

The oxidation product of starch may conveniently be used as a binding additive for paper, as a builder for detergents, as a polyelectrolyte thickening agent, in formulations for paints and printing inks, and as a high-molecular-weight coalescent.

Its use as a builder for detergents is particularly advantageous by virtue of its good sequestering properties combined with the biodegradability of the product compared with products oxidised by hypochlorite.

Additionally the product may be used as a co-builder in detergent formulations in association with known builders, such as zeolites, in order to improve the anti-redeposition properties and dispersion capacity of the detergents and achieve an improved soil removal effectiveness.

Hydrolysis products of starch and particularly dextrin oxidised by the method of the invention may also be used in particular as polyelectrolyte thickening agents in formulations for paints and printing inks. These uses constitute a further subject of the invention.

CLAIMS

1. A method of oxidising carbohydrates, characterised in that the oxidation is effected by means of an oxygen containing gas in an alkaline aqueous medium in the presence of a catalytic quantity of a metal ion selected from the metals of group VIII of the periodic table, copper and silver and a substance which acts as a ligand for the metal ion.

2. A method according to Claim 1, characterised in that the ligand is a polydentate amine ligand.

3. A method according to Claim 2, characterised in that the ligand is a monoamine of the general formula:



in which one of the radicals R_1, R_2 and R_3 is selected from the group consisting of hydrogen, C_1-C_4 alkyl groups and carboxyalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms and the rest of the R_1, R_2 and R_3 radicals are the same or different carboxyalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms.

4. A method according to Claim 2, characterised in that the ligand is a polyamine of the general formula:



in which R is a C_1-C_4 alkylene group, preferably ethylene, and

R_1, R_2, R_3, and R_4 are the same or different and are selected independently of each other from the group consisting of hydrogen, C_1-C_4 alkyl groups, aminoalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms and carboxyalkyl radicals in which the alkyl group has from 1 to 4 carbon atoms,

or alternatively, R_1 and R_2 and/or R_3 and R_4 form a heterocyclic ring with the respective nitrogen atom,

or alternatively, R_1, R_2, R_3 and R_4 form heterocyclic groups with the respective nitrogen atoms.

5. A method according to Claim 2, characterised in that the amine ligand is selected from the group consisting of nitrilotriacetic acid, iminodiacetic acid, ethylenediamine, diethylenetriamine, triethylenetetramine, ethylenediaminetriacetic acid, ethylenediaminetetra-acetic acid, phenanthroline and 2,2'-dipyridyl.

6. A method according to Claim 5 in which the ligand is ethylenediaminetetra-acetic acid and the metal ion is iron.

7. A method according to Claim 5 in which the metal ion is copper and the ligand is o-phenanthroline.

8. A method according to Claim 1 in which the molar concentration of the metal ion in the reaction medium is from 1 to 0.25% with reference to the number of moles of glucoside in the oxidation substrate.

9. A method according to Claim 1 wherein the oxidation reaction is carried out at a temperature of from 25 to 90°C and at atmospheric pressure with vigorous stirring.

10. A method according to Claim 1 wherein the carbohydrate subjected to oxidation is selected from starch, dextrin, hydrolysis products of starch or dextrin, and sorbitol.

11. An oxidation product of starch, a hydrolysis product of starch or dextrin obtainable by a method according to any one of Claims 1 to 9.

12. The use of an oxidation product of starch, a hydrolysis product of starch or dextrin obtainable by a method according to any one of Claims 1 to 9 as a builder or co-builder for detergents.

13. The use of an oxidation product of starch, a hydrolysis product of starch or dextrin obtainable according to any one of Claims 1 to 9 as a binder for paper, as a polyelectrolyte thickening agent or as a coalescent.


100
%T
80
60
40
20
0
4000
3500
3000
2500
2000
1750
1500
1250
1000
750
400
CM-1
1
2

INTERNATIONAL SEARCH REPORT

International Application No PCT/EP 92/00827

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all)[6]

According to International Patent Classification (IPC) or to both National Classification and IPC

Int.Cl. 5 C08B31/18; C07H7/033; C11D3/22; D21H17/28

II. FIELDS SEARCHED

Minimum Documentation Searched[7]

Classification System	Classification Symbols
Int.Cl. 5	C08B ; C07H

Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched[8]

III. DOCUMENTS CONSIDERED TO BE RELEVANT[9]

Category °	Citation of Document,[11] with indication, where appropriate, of the relevant passages[12]	Relevant to Claim No.[13]
X	US,A,3 736 224 (M. GRAYSON ET AL.) 29 May 1973 see abstract see column 2, line 24 - line 28 see column 2, line 51 - column 3, line 8 see claims; examples 12,18; table II	1,2,9
A	EP,A,0 232 202 (ROQUETTE FRERES) 12 August 1987 see claims	1,9,10, 12,13
A	US,A,3 873 614 (LAMBERTI V. ET AL.) 25 March 1975 see abstract see column 8, line 39 - line 47; examples 20,21	1,9,10, 12
A	EP,A,0 378 127 (HOECHST AKTIENGESELLSCHAFT) 18 July 1990 see page 2, line 41 - line 47 see page 3, line 48 - line 50; claims; example 1	1,12

-/--

° Special categories of cited documents :[10]

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report
17 JULY 1992	24. 07. 92
International Searching Authority	**Signature of Authorized Officer**
EUROPEAN PATENT OFFICE	MAZET J.

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)

Category °	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	EP,A,0 247 314 (HÜLS AKTIENGESELLSCHAFT) 2 December 1987 see line 40 - line 49 see page 4, line 1 - line 3	1,2,4
A	US,A,4 572 798 (KOTHS ET AL.) 25 February 1986 see column 5, line 38 - line 40	1,2,5,7

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO. EP 9200827 SA 59308

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 17/07/92

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
US-A-3736224	29-05-73	None		
EP-A-0232202	12-08-87	FR-A-	2597473	23-10-87
		CA-A-	1284496	28-05-91
		DE-A-	3773009	24-10-91
		JP-A-	62247837	28-10-87
		US-A-	4985553	15-01-91
US-A-3873614	25-03-75	CA-A-	959047	10-12-74
		DE-A-	2233977	01-02-73
		FR-A,B	2145722	23-02-73
		GB-A-	1385403	26-02-75
		NL-A-	7209737	16-01-73
		SE-B-	395008	25-07-77
EP-A-0378127	18-07-90	DE-A-	3900677	19-07-90
		AU-B-	617919	05-12-91
		AU-A-	4782490	19-07-90
		CA-A-	2007550	12-07-90
		JP-A-	2233691	17-09-90
		US-A-	5082504	21-01-92
EP-A-0247314	02-12-87	DE-A-	3617187	26-11-87
		JP-A-	62285918	11-12-87
		US-A-	4734485	29-03-88
US-A-4572798	25-02-86	AU-B-	594930	22-03-90
		AU-A-	5005285	12-06-86
		CA-A-	1248300	03-01-89
		EP-A-	0185459	25-06-86
		GB-A,B	2168055	11-06-86
		JP-A-	61140600	27-06-86